

CONTEGA SOLIDO SL-D

Full-surface adhesive window sealing tape for interior use with an additional adhesive zone on the fleece side



Technical data

Substance		
Backing	PP backing fleece, PP copolymer special membrane	
Adhesive	modified waterproof SOLID adhesive / special acrylate adhesive	
Release film	one or two split silicone-coated PE sheet	
Attribute	Regulation	Value
Colour		white
sd-value	BS EN 1931	2.8 m
g-value		14 MNs/g
Can be plastered over		yes
ift Rosenheim (DE) testet	MO-01/1:2007-01, Abs. 5	passed, surrounding
Application temperature		above -10 °C ; 14 °F
Temperature resistance		permanent -40 °C to 90 °C ; -40 °F to 194 °F
Storage		cool and dry

Area of application

The CONTEGA SOLIDO SL-D joint adhesive tape, which is full-surface adhesive and can be plastered over, ensures interior airtight and vapour-retarding sealing of windows and doors to adjacent building components made of wood and mineral substrates such as concrete and masonry. The integrated adhesive zone on the fleece side makes it easy to seal joints to windows and doors.

The stuck joint is immediately airtight and can be subjected to loading. The fleece can simply be plastered over in accordance with our application guide.

These bonds will correspond to the requirements of DIN 4108-7, SIA 180 and OENORM B 8110-2.

Forms of delivery

Art. no.	GTIN	Length	Width	Weight	PU	Container
15985	4026639159854	30 m	100 mm	1.4 kg	8	288
16038	4026639160386	30 m	80 mm	1.1 kg	8	288

Advantages

- ✓ Full-surface adhesive, the joint is immediately airtight and can be subjected to loading
- ✓ Extremely strong adhesion on mineral substrates too thanks to modified waterproof SOLID adhesive
- ✓ Can be plastered over
- ✓ The integrated adhesive zone on the fleece side makes it easy to seal joints to windows and doors
- ✓ Easy to apply
- ✓ Lowest VOC rating in hazardous substance test

Substrates

Before sticking, substrates should be brushed off, wiped clean with a cloth or cleaned using compressed air.

Uneven mineral substrates may need to be levelled with a smooth finish.

Adhesion to frozen surfaces is not possible. There must be no water-repellent substances (e.g. grease or silicone) on materials to be bonded. Substrates must be sufficiently dry and have sufficient load-bearing capacity.

Permanent adhesion is achieved on all pro clima interior membranes and on other vapour retarder and airtight membranes (e.g. those made of PE, PA, PP and aluminium).

Adhesion can be carried out on planed and painted wood, hard plastics, hard wood-based panels (chipboard, OSB and plywood panels) and on mineral substrates such as concrete and masonry.

The best results in terms of structural stability are achieved on high-quality substrates.

It is your responsibility to check the suitability of the substrate; adhesion tests are recommended in certain cases.

Pretreatment with TESCON PRIMER RP is recommended in the case of substrates with insufficient load-bearing capacity.

The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about application and construction is given in the pro clima planning documentation and application recommendations. If you have any questions, please call the pro clima technical hotline Ireland and UK:
Phone: +353 46 9432104
Fax: +353 46 9432435
info@ecologicalbuildingsystems.com

For Stockists contact
Ireland
T. 046 9432104
F. 046 9432435
UK
T. 01228 711 511
F. 01228 712 280

Ecological Building Systems
info@ecologicalbuildingsystems.com

www.ecologicalbuildingsystems.com




General conditions

The bonds should not be subjected to tensile strain.

Press firmly to secure the adhesive tapes, taking care to ensure that there is sufficient resistance pressure behind them.

Airtight seals can only be achieved if the sealing tape is installed free of folds and breaks.

Ventilate continuously and systematically to prevent build-up of excessive humidity; use a dryer if necessary.



Prüfbericht Nr. 15-003305-PR01
(PB-E03-020310-de-02)

- CONTEGA SOLIDO SL-D
 - CONTEGA SOLIDO EXO-D
- nach MO-01/1:2007-01, Abs. 5
15.03.2016



* Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classes allant de A+ (très faibles émissions) à C (fortes émissions)

The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about application and construction is given in the pro clima planning documentation and application recommendations. If you have any questions, please call the pro clima technical hotline Ireland and UK:
Phone: +353 46 9432104
Fax: +353 46 9432435
info@ecologicalbuildingsystems.com

For Stockists contact
Ireland
T. 046 9432104
F. 046 9432435
UK
T. 01228 711 511
F. 01228 712 280

Ecological Building Systems
info@ecologicalbuildingsystems.com

www.ecologicalbuildingsystems.com

